

**FP LUKS ANTILOP (MV)**

TEST TYPES / TEST TİPİ	ASPECT / KRİTER	NORM	UNIT / BİRİM	STANDART TEST
WEIGHT / AĞIRLIK		390±%5	gr/m <sup>2</sup>	ISO 2286-2
TEAR STRENGTH / YIRTILMA	ACROSS / EN	>30	N	ISO 4674-1
	ALONG / BOY	>30		
TENSILE STRENGTH / KOPMA	ACROSS / EN	>300	N	ISO 1421
	ALONG / BOY	>450		
ELONGATION AT BREAK / UZAMA	ACROSS / EN	70±%20	%	ISO 1421
	ALONG / BOY	90±%20		
ADHESION / LAMİNASYON YAPIŞMASI □		>10	N	ISO 13937-2
ABRASION RESISTANCE AŞINMA DAYANIMI	30.000 Rub (12 kpa)	≥5,0	GRADE	ISO 12947-2
PILLING TEST - PILLING TESTİ	10.000 Rub (12 kpa)	≥5,0	GRADE	ISO 12945-2
COLOR FASTNESS TO RUBBING / SÜRTÜNME RENK HASLIĞI	DRY / KURU	≥5,0	GS	ISO 105X12
	WET / ISLAK	≥4,0	GS	
LIGHT FASTNESS IŞIK HASLIĞI	LIGHT COLORS / AÇIK RENKLER	≥4,0	GS	ISO 105-B02
	DARK COLORS / KOYU RENKLER	≥3,0	GS	

**COMPOSITION - İÇERİK**

SURFACE - YÜZEY	%100 POLYESTER
BACKING - ZEMİN	%100 POLYESTER

Arma Kumaş Ve Perde A.Ş  
Orta Mahalle Numunebağı CD No : 64 - 66 / A Bayrampaşa / İstanbul

Phone / Telefon : +90 212 613 97 75

E-mail : arma@armakumas.com.tr

www.armakumas.com.tr